





Lys refleksjon



Lys brytning



Brytningsindeks for noen stoffer

Luft	1,0003
Vann	1,33
Is	1,31
Pleksiglass	1,48
Kronglass	1,51
Kvartskrystall	1,54
Plast (polystyren)	1,59
Flintglass	1,61
Diamant	2,42

Verdiene varierer (til dels betydelig) med fysiske betingelser som renhet, trykk osv.

